



Shenzhen **BTREE** Industrial Co., Ltd

Tel: 0086-755-29652402 Fax: 0086-755-29184920

Email: englishsales88@btree.cn URL: www.szbtree.com

H2310 Antistatic Agent

High Performance Type

Physical Properties

Appearance	Light blue and transparent liquid
Ion Type	modified cationic
PH Value	6-8
Dissolvability	Ethanol, water

Coating Effect

After coating, PE surface is dry, surface resistance can reach $10^8-9\Omega$, anti-static performance is steady, anti-static effect can last more than half year.

Application For PET Film anti-static purpose

Coating Method Roller coating or spraying



Tel: (86)-755-29652402 www.szbtree.com email: englishsales88@btree.cn

Factory Address: A2 Bldg, Huafeng Industrial Park, Zhongxing Rd., West Lake Village, Qiuchang Town, Huizhou, Guangdong China 516221

Office Address: Room 1016, Nuobo Plaza, 269#, Qianjin Rd., Bao An District, Shenzhen Guangdong China 518100