



BTREE

Shenzhen **BTREE** Industrial Co., Ltd

Tel: 0086-755-29652402 Fax: 0086-755-29184920

Email: englishsales88@btree.cn URL: www.szbtree.com

Permanent ESD Pink PE Bag

Data Sheet

Item	Test Method	Unit	Result
Surface resistance	ESD STM 11.11	Ω	10^8 - 10^{11} (permanent)
Static dissipative	5000~0V	s	<5
Melt Flow Rate	D 1238	g/10min	2.1
Water absorption	D 570	%	0.5
Density	/	g/cm	0.92
Tensile Strength	D 882	Mpa	TD: 16.01 MD: 17.75
elongation at break	D 882	%	TD: 700 MD: 685
Coefficient			Outer surface: 0.09 Inner surface: 0.08
Heat Seal Temperature	/	F	250-375
Thickness			$\pm 10\%$
Length			$\pm 3\text{mm}$
Width			$\pm 2\text{mm}$
Appearance			Pink

Tel:(86)-755-29652402 www.szbtree.com email:englishsales88@btree.cn

Factory Address: A2 Bldg, Huafeng Industrial Park, Zhongxing Rd., West Lake Village, Qiuchang Town, Huizhou,Guangdong China 516221

Office Address: Room 1016, Nuobo Plaza, 269#, Qianjin Rd., Bao An District, Shenzhen Guangdong China 518100